



PROCESSING INSTRUCTIONS

KAMBA Floor **Your anti-slip coating for all floor covering** Item number 16300 / 16350

Important note:

During coating and for 12 hours afterwards, ensure that the surface temperature is above 15°C!

Before use, observe the safety instructions on the respective labels!

In our safety box, you will find everything you need for YOUR SLIP RESISTANCE in accordance with DIN 51130:

For the first steps, we recommend that you wear household gloves

1. Removal of all limescale residues:
Wet the surface with warm water.
Then clean thoroughly with a floor cleaner and a sponge.
Rub the surface dry and keep it completely dry for 12 hours
Pro tip: Avoid direct sunlight and do not apply outdoors if there is a risk of rain when using Kamba Floor
2. Limit the area to be coated with the enclosed adhesive tape.
3. Place the special roller on the roller bracket
4. Shake KAMBA anti-slip vigorously (>2 min.) The quantity is sufficient for approx. 2 m².
5. Pour the required amount into the enclosed coating tray.
6. Dip the special roller into the coating material; roll out any excess material until the roller is evenly saturated and no longer drips.

KAMBA Floor

適用於所有地面覆蓋物的防滑塗層

重要注意事項：

塗佈期間及後續12小時內，請確保
表面溫度維持在15°C以上！

使用前請詳閱各標籤上的安全說明！

我們的安全防護盒內含符合 DIN 51130 標準的
全方位防滑解決方案：

初次操作時建議配戴家用防護手套

徹底清除水垢殘留：

以溫水浸濕表面

使用地板清潔劑與海綿徹底擦拭

擦乾表面並保持完全乾燥12小時

專業提示：使用Kamba Floor時避免陽光直射，若戶外有降雨風險請勿施作

使用隨附膠帶標示需塗佈區域

將專用滾筒安裝於滾筒支架

用力搖晃KAMBA防滑劑 (>2分鐘)。此用量約可塗佈2平方米。

將所需量倒入隨附塗料托盤。

將專用滾筒浸入塗料中；滾壓去除多餘塗料，直至滾筒均勻飽和且不再滴落。

7. Begin coating. Always work from the center of the surface outwards. First coat the surface evenly and thinly in one direction then, at a 90° angle, spread the already applied material again with the roller; again at a 90° angle (without applying pressure to the roller)
Pro-Tip: during the last pass without pressure on the roller.
8. Please remove the adhesive tape immediately after coating.
9. Any unused anti-slip coating material can be poured back into the bottle. The bottle is tightly sealed and can be stored at cellar temperature for approx. 3 months.
10. Wash all tools thoroughly with lukewarm water for reuse
11. After 12 hours of drying time, your floor is ready for use again.
(Optimal conditions: temperature > 20°C and good ventilation!)
12. Mechanical cleaning may only be carried out after 3 days of drying

We are happy to assist you with any problems. Simply send an email to info@kamba-antirutsch.de

開始塗佈。務必從表面中心向外作業。
先沿單一方向均勻薄塗表面，
接著以90°角度重新滾壓已塗佈的材料；
再次以90°角度滾壓（無需施壓滾筒）。
專業提示：最後一道工序時請勿施壓滾筒。
塗佈完成後請立即移除膠帶。
未使用完的防滑塗料可倒回原瓶。
瓶口密封後可於室溫環境保存約3個月。
所有工具請以溫水徹底清洗後可重複使用
經12小時乾燥後，地板即可重新使用
(最佳條件：溫度>20°C且通風良好！)
機械清潔須待乾燥3日後方可進行